

**MERMET**

## DESCRIPTION FOR TENDER DOCUMENTS

### **ACOUSTIS® 50 - ACOUSTIC ABSORPTION FABRIC FOR INTERNAL APPLICATION**

from Mermet Acoustics range or equivalent

Excellent acoustic absorption:  
helps to enhance acoustics whilst blending perfectly with the interior design

Composition: coated fibreglass fabric

Weight/m<sup>2</sup>: **420 gr** ± 5%

Thickness: **0,50 mm** ± 5%

Fire classification:

**M1** (NFP 92 503), **BS** (476 Pt 6&7 Class 0),  
**Euroclass** C-s3-d0 (EN 13501-1)


Higher heating value (ISO 1716):

**15,7 MJ/kg** (6,59 MJ/m<sup>2</sup>)

### **Greenguard® Gold**

Acoustic absorption factor **α<sub>w</sub>: 0,35 to 0,8** depending application  
**6 colours** available

### **ACOUSTIS® 50**



For more information about blinds and mechanisms,  
contact us on +33 (0)7 61 12 63 96 or [Click Here](#)

*This data have no contractual value (V1 2021).*



Mermet SAS  
58 Chemin du Mont Maurin  
38630 Les Avenières - Veyrins-Thuellin

[contact@sunscreen-mermet.com](mailto:contact@sunscreen-mermet.com)

Tel. +33 (0)474 336 615

Fax. +33 (0)474 339 729

[www.sunscreen-mermet.com](http://www.sunscreen-mermet.com)

